

Carbon Quantum Dots in Healthcare: A Promising Solution for Sustainable Healthcare and Biomedical Practices

Kokkonda Jackson Sugunakara Chary¹, Anuradha Sharma^{2,*}, Amrita Singh³

¹Department of Biotechnology, Lovely Professional University-144001, Punjab India

^{2,*} Department of Molecular Biology & Genetic engineering, Lovely professional University-144001, Punjab India

³Department of Biotechnology and Medical Engineering, National Institute of Technology, Rourkela

*Correspondence to: s.anuradha21@ymail.com; anuradha.28927@lpu.co.in

Abstract. The pursuit of sustainable development refers to meet the present needs while safeguarding the resources for future generations ensuring the well-being of human societies. Nanoscience is contributing significantly to the field of public healthcare by delivering a number of cutting-edge technological applications and products related to healthcare. Carbon quantum dots (CQDs), carbon-based nanomaterials, are gaining recognition for their potential health benefits worldwide. The current study aims to review the applications of CQDs in the biomedical field based on existing literature. The methodology used is the collection of the literature studies from authoritative sources such as Google Scholar, PubMed, and ResearchGate, with keywords ‘Carbon quantum dots in healthcare, biosensing, bioimaging, gene therapy, treatment, and theranostics’. The retrieved literature was comprehensively analyzed to construct the detailed review which suggests that CQDs have demonstrated remarkable potential across various domains, from disease treatment to biosensing, gene delivery, drug delivery, and bioimaging thus helping to achieve the 3rd goal of sustainable development. In addition to CQDs synthesized by chemical processes, natural CQDs developed by green chemistry from natural sources are gaining accreditation due to their evidenced potential health benefits. This article has reviewed the versatile applications of Carbon Quantum Dots (CQDs) in the biomedical field and discussed the possible contributions to achieve sustainable healthcare for the first time, suggesting CQDs as a potential target for future research and development. However, there are some limitations of CQDs including complex surface modification, toxicity, limited clinical translation which requires more attention in order to improve their healthcare applicability.

Keywords: Carbon Quantum Dots (CQDs), Healthcare, Nanoscience, Public health, Sustainable development goal (SDG 3), Theranostics, Wellbeing

1 Introduction

Synthetic chemistry and nanotechnology are playing an important role in today’s health and medicinal field. As a key growth sector and continuously evolving field, sustainable practices are a must to be employed in global health care. A sustainable healthcare system can be defined as a system fulfilling the medical needs of the current generation by providing high-quality care and exerting minimal damage to the environment [1-3]. Drugs with significant toxicity, high costs, limited availability, improper diagnostic techniques, emerging infectious diseases, microbial drug resistance, treatment of fatal diseases, and biomedical waste are some of the factors that significantly block the way to achieve Sustainable Development Goal 3 (SDG 3) i.e. healthcare and wellbeing. Development of new tools, technologies, and therapeutic candidates with minimal side effects are warranted as possible alternatives to deal with challenges of healthcare sustainability [1-5].

The cutting-edge research and technological advancements in the field of nanotechnology, commonly known as nanomedicine, have shown a remarkable potential to address the healthcare sector challenges along with the promises of cost reduction and affordability in an eco-friendly manner [6]. Nanomaterials play a prominent role in the treatment of diseases, target drug delivery, electrochemical sensing, gene delivery, biomarker detection, food analysis-related sensing, and biosensing [7]. Quantum dots, polymeric nanoparticles, dendrimers, liposomes, metallic nanoparticles, carbon nanotubes, and micelles are just a few examples of different nanomaterials that have been extensively studied

for their therapeutic potential against complex diseases [8]. Currently, there are many FDA-approved therapeutic nanoparticles, which were created by combining chemotherapeutic drugs with polymeric nanoparticles [9]. Nanoscience has recently grown and expanded tremendously and has become extremely influential in all disciplines of modern study, promising improvements in public health and causing notable changes in living and well-being. Nanotechnology is known as the medicine of the future [10]. A better understanding and the use of nanoparticles pave the path for the future development of innovative materials that may enhance health and quality of life. In the future, it is projected that the demanding scope will increase due to the betterment of health using a distinctive combination of nanomaterials and sustainability [11].

Carbon quantum dots (CQDs) hold a paramount significance in the realm of biomedical research, with their versatile applications spanning bioimaging, biosensing, drug delivery, gene delivery, and a host of therapeutic possibilities [7]. This narrative review paper compiles insights from various studies to elucidate the multifaceted role of CQDs in these domains. In bioimaging, CQDs serve as exceptional contrast agents, enabling precise and non-invasive visualization of biological structures. Their exceptional photoluminescent properties make them invaluable in biosensing, facilitating the detection of specific biomolecules and environmental contaminants with high sensitivity. CQDs' potential in drug delivery is a game-changer, allowing targeted and controlled release of therapeutic agents to enhance treatment efficacy while minimizing side effects. Moreover, their capacity for gene delivery holds promise in gene therapy, a cutting-edge field with transformative potential for genetic diseases [7-8,10].

Research on Carbon Quantum Dots (CQDs) has made significant strides, particularly in the context of green synthesis and biomedical applications. However, notable research gaps exist in these areas. In the domain of green synthesis, there is a need for more comprehensive studies exploring novel, sustainable methods of CQD production. While natural CQDs synthesized through green chemistry show promise, there is a dearth of standardized protocols and a limited understanding of their full potential [7]. Furthermore, in the realm of biomedical applications, the challenge lies in optimizing CQDs for specific therapeutic and diagnostic purposes. Tailoring CQDs to target particular diseases, improving their drug delivery efficiency, and enhancing their biocompatibility requires further investigation. Bridging these research gaps in green synthesis and biomedical applications of CQDs is pivotal for harnessing the full potential of these nanomaterials in sustainable healthcare and biomedicine [6-11]. The current article aims to summarize the biomedical applications of Carbon Quantum Dots (CQDs) on the basis of existing literature and their implication for sustainable development, and thus lays the foundation for future research and underscores CQDs' vital role in advancing the frontiers of biomedical science including diagnostics and treatment therapy.

2 Carbon quantum dots

Carbon quantum dots (CQDs) are recently discovered carbon nanomaterials that have accumulated apt interest as potential competitors to the traditional semiconductor quantum dots. These CQDs have promising applications in biosensing, bioimaging, drug delivery, electrochemical sensing, gene delivery, biomarker detection, food analysis-related sensing, treatments of diseases as well as in various drug formulations (**Fig. 1**). High tunable fluorescence along with low toxicity, high stability, resistance to photobleaching and more cellular compatibility are some of the properties due to which CQDs are more preferred over conventional semiconductor-based quantum dots (SQDs) [12]. From a structural point of view, CQDs possess unique particulate structures in the nanometer size range (<10nm), where carbon atoms are generally arranged in graphene-like hexagonal structures. These nanoparticles can be synthesized via multiple strategies including hydrothermal treatment, chemical oxidation, pyrolysis of carbon precursors and microwave aided synthesis. CQDs can be further modified by multiple carbonizations and polymerizations to control their chemical attributes, surface functionalization, passivation, fluorescence tuning, and other physical and biological properties. Carbon nanotubes, fullerenes, graphene sheets, and nano-diamonds are some other advanced carbon-based nanomaterials over which CQDs are superior due to their distinct shapes with superfine dimensions, modifiable functional groups over the surface with cheap and rapid synthetic preparations [12].




Fig. 1 Biomedical Applications of Carbon quantum dots

3 Biomedical Applications of CQDs

3.1 CQDs and Bioimaging:

Bioimaging is an evolving tool of biomedicine that is associated with the development of various imaging techniques to facilitate the visualization of internal organs and characterization of cellular and molecular processes inside living organisms without posing significant disturbance to the internal system [13]. Nanomaterials like CQDs can be conjugated with proteins, peptides, antibodies, or other small molecules to track the cancer cells to detect some biomarkers, or for drug delivery. Iron oxides used for MRI is one of the important examples where CQDs have been used in clinical setting. CQDs have been reported to be safe for bioimaging in various *in vitro* and *in vivo* setups. Semiconductor quantum dots (SQDs) such as Cadmium, Selenium containing QDs which are the older alternatives for bioimaging are associated with a few limitations like considerably large size, cellular accumulation, toxicity due to synthesis with heavy metals as well as blinking (fluctuating fluorophore emission which limits the application at single particle level). CQDs, however, are considerably superior nanomaterials for cellular and bioimaging due to their better biocompatibility, low toxicity as well and no-blinking properties [14,15].

Graphene quantum dots (GQDs), a type of CQDs, were first time reported to be used in cancer cell imaging by [16], where these QDs exhibited stable fluorescence emission. Various CDs synthesized from natural precursors were further reported to be tested for cellular imaging properties in different cell lines of breast cancer (T47D, MCF-7) as well as cervical cancer (HeLa) [17,18,19]. The investigated CQDs-graphene QDs, Boron doped GQDs, and linseed derived CQDs exhibited negligible toxicity, considerable solubility in water, photo-bleaching resistance, and superior biocompatibility. The property of having a small size (less than 10nm) enables CQDs to probe small biological entities [20]. In an attempt to develop CQDs with strong luminescence, Cao *et al.* used poly (propionyl ethylenimine-co-ethylenimine) for surface passivation and two-photon excitations to synthesize water-soluble CQDs with small size (~5nm). These CQDs were able to tag the cell membrane and cytoplasm but were unable to reach the nucleus when incubated with MCF-7 cells as suggested by observation under fluorescence microscope. Tagging of these CQDs with an HIV-1 derived translocation protein TAT (Trans-Activator of Transcription) may enable the probing of the nucleus by overcoming the hurdles associated with the cell membrane and by enhancing the labeling efficiency within the cells [21].

CQDs are beneficial in regenerative therapy where stem cells are used to form different tissue-specific cells after differentiation, and CQDs have been successfully demonstrated to efficiently label different kinds of stem cells like pancreas progenitors, cardiac progenitors as well as neurosphere cells. This stable, long-term term, and non-toxic CQD-facilitated imaging of stem cells in regenerative medicine helps to understand the stem cell contribution, migration, and development into regenerative tissue [22-24]. Graphene Quantum Dots were also used to label human neural stem cells (hNSCs) without affecting the self-renewal capacity as well as the expression of specific hNSC markers [25]. GQDs synthesized using Rhodamine derivative were also reported to be useful in cancer stem cell imaging [26].

CQDs have also been explored for their utility in *in vivo* bioimaging. Hydrothermally generated CQDs of 2-5nm size and passivated with urea were applied for optical imaging in L929 fibroblasts as well as in mice [27]. These CQDs exhibited low cytotoxicity and remarkable performance as bioimaging tools. Various studies demonstrated the synthesis of CQDs for *in vivo* imaging and suggested that longer wavelength-based excitation is preferred due to the deeper penetration required for specimen imaging [28,29,30]. CQDs synthesized by Li *et al.* (2017) when injected intravenously exhibited tumor-selective fluorescence with comparatively very low or no fluorescence signals in normal

tissues. Tumor-specific fluorescence was due to folate-based specific targeting of tumor area by tested IR70/ folic acid functionalized GQDs [31].

CQDs are also being considered as a promising candidate for per-acoustic imaging with deeper tissue penetration and high resolution. Radiotracers ¹²⁵I-F56 Peptide and ⁶⁸Ga-DOTA-PA1 targeting VEGFR1 and Somatostatin receptor 2 respectively were synthesized and shown to be promising diagnostic agents in PET scanning of gastric tumors as well as lung cancers [32,33].

3.2 CQDs and Biosensing

Biosensors aid early disease diagnosis which improves the chances of successful treatments. These biosensors measure the organic/ inorganic and bio-molecules in living systems and have applications in various fields like biomedicine, food safety, agriculture or industrial monitoring [34]. The detector part of biosensors is majorly based on bio-receptors (like enzymatic, nucleic acid, biomimetic, cellular based and immunosensors). CQDs as biosensors has been devised for monitoring of various metabolites like nucleic acids, glucose, phosphate ions, potassium ions, iron and cellular pH [12]. These biosensors exhibit various kinds of interactions like π - π conjugation, electrostatic interactions or electron transfers, which facilitates turn on-off status of quantum dots. Additionally, CDs and CQDs offer wonderful electrical conductivity, enhanced dispersibility and large surface area which enable the stable interaction with target biomolecule, thus acting as excellent fluorescent biosensing probes. For example, Rhodamine-functionalized graphene quantum dots (RBD-GDQs) were used as iron detecting biosensors in cancer stem cell membranes [26]. CDQs can also be used for detection of other metal ions and free radicals like peroxy nitrite [35, 24]. Reactive oxygen species (ROS), also known as free radicals serve as important biomarkers for DNA damage, inflammation, infections, arthritis, neurodegeneration or cancers and to sense the drug efficacy. Bhattacharya *et al.* developed an ascorbic acid containing hydrogel based CQDs for ROS sensing and used for evaluation of the chemotherapeutic drug efficacy by measuring the ROS levels after drug administration [36].

In another study, Lu *et al.* demonstrated the synthesis of CQDs using one-pot pyrolysis method for detection of β -glucuronidase inhibition. β -glucuronidase is used as a biomarker in cancers and its inhibition is associated with controlled proliferation of cancer cells. Reduced β -glucuronidase activity leads to changed fluorescence intensity of CQDs [37]. There are other reports of CQDs usage for detection of Glutathione (GSH) levels and intracellular pH changes in cancer cells (cancer cells exhibit comparatively acidic pH) [38, 39]. Raveendran and Kizhakayil designed mint based Green CQDs, which can sense folic acid levels. Folic acid deficiency is associate with several disease conditions like neural tube defects, mental retardation and stroke, so tracing this analyte is crucial in biomedical setup [40]. Additionally, CQDs can facilitate the residual antibiotic sensing in milk, milk products or other environmental targets

Due to high stability and good electrical conductivity, CQDs have also been used to develop electrochemical sensors for detection of molecules like cholesterol, nucleic acids, oval-albumin, glucose, ascorbic acid, L-cysteine etc. Polymeric CQDs further exhibited high sensitivity and specificity for hemoglobin detection [41].

3.3 CQDs and Efficient Drug delivery

Major cancer therapeutics include chemotherapy, radiotherapy or surgical resection all of which are associated with multiple side effects. Chemotherapy is associated with non-specific killing of tumor as well as normal cells due to lack of precision and thus results in drug toxicity as well as multiple drug resistance. Controlled drug delivery to a specific site may deal with these limitations of otherwise effective chemotherapeutic drugs. CQDs have been proposed as efficient drug carriers containing bioimaging systems and specific drug delivery with low cytotoxicity as compared to conventional chemotherapeutics [18]. CQDs containing surface amino acids, which enables cross linking with tumor therapeutic as well as diagnostic candidates. CQDs prepared from citric acids using microwave pyrolysis and Schiff's base linkage delivered the therapeutic molecules in tumor microenvironment in a controllable manner [41].

Targeted drug delivery in nucleus and mitochondria has also been exhibited by CQDs prepared by hydrothermal method [42]. Additionally, these carbon dots have also been utilized to differentiate the normal and apoptotic cells of A549 cell line, and to deliver the anticancer drug to the targeted areas of MCF-7. These CQDs showed less toxicity when used to deliver anticancer drug to normal HepG-2 cells [43,44].

Not only in cancer studies, drug delivery science is looking for development of such systems, which will improve the retention, absorption and elimination related parameters of the drugs, otherwise facing low efficacy due to poor delivery at target or fast elimination by metabolic system. Khan *et al.* designed CQDs for controlled delivery of drug named Dopamine Hydrochloride (DH) (Hydrochloride salt of a neuromodulatory molecule-Dopamine) to target the neuro-related ailments [45]. CQD-DH conjugates were shown to efficiently deliver the drug for extended periods without exerting any toxicity both in *in vitro* and *in vivo* model systems. CQDs designed for performing multiple

functions like delivery of signaling molecules/ magnetic/ MRI agents along with drugs or dual drug delivery have also been reported. A pH-sensitive CQD for dual delivery of doxorubicin and heparin was reported by Zhang *et al.*, which showed more specific drug release to the cancer cells. Doxorubicin is an anticancer drug that otherwise is associated with various side effects due to non-specific delivery, whereas, heparin is used to suppress high blood coagulation and venous embolism in cancer patients [46].

Natural CQDs derived from different plant species like *Curcuma longa*, *Ocimum sanctum*, *Aloe vera*, *Azadirachta indica* etc. are gaining accreditation in drug delivery as compared to the synthetic conventional CQDs due to their properties like greater abundance, more biocompatible and environment friendly nature as well as solubility in aqueous fractions. The diverse functional groups over the surface of natural CQDs improve the optical properties, sensing and biosensing functions along with the drug delivery. These CQDs are being used to deliver drugs with the potential to treat cancers, neurodegenerative diseases as well as microbial infections (**Table 1**) [47].

Table 1. Discusses the different types of natural CQDs being used for drug delivery and disease treatment [48-67]

Name of CQD	Size	Applications
<i>Aloe vera</i>	5nm	Anti-proliferative, Wound healing
Ascorbic acid	2nm	Promoting capillary elasticity, lowering blood cholesterol levels & boosting immunity.
Curcumin	5.4 –7.0nm	Anti-bacterial, Wound healing & Anti-tumor
Citric Acid, dicyandiamide	2.5 nm to 3.8 nm	Biosensing
Carrot juice	3.75nm	Cellular imaging
Orange Juice	1.5- 4.5nm	Biosensing
Hair	4.56nm	Bioimaging
Neem leaves	1.5- 2.5nm	Bioimaging, antioxidants & antimicrobial
Tulasi leaves	3-7nm	Antimicrobial
Wheat straw	5.7nm	Drug delivery, biosensors, bioimaging, and photocatalysis
Onion waste	1-7nm	Biocompatibility, good photostability, low cytotoxicity & high photocatalytic activity
Bamboo leaf cellulose	2 nm	Anti-cancer
Coconut husks	2nm	Targeted drug delivery & bioimaging
Rice residue	5-10nm	Soil contamination, Water & air pollution control
Coffee ground	1.6-4.4nm	Necro apoptosis
Prawn shell	---	Bio-imaging & antibacterial
Pasteurized milk	10 nm	Hypertension & renal problems
<i>Chrysanthemum</i> buds	3.45 nm	Photocatalytic activity
Saffron	1.5 – 3.0 nm	Local anaesthetic
Mulberry leaves	1-2 nm	Anticancer

3.4. CQDs and Disease Treatment

CQDs have also gained enormous attention in the therapeutics field as multiple reports emerged suggesting specifically designed carbon dots targeting various diseases in last decade (**Figure 2**)




Fig. 2 Use of CQDs in the treatment of various diseases

Nanomaterials propose comparatively simple surface therapy for different infectious pathogens like viruses, bacteria, fungi, or parasites by photodynamic therapy. During photodynamic inactivation CQDs with photosensitization capacity generate ROS in microbes by utilizing molecular oxygen, thus inactivating those pathogens [68]. Polyamine-based CQDs were designed and demonstrated to exhibit antibacterial potential against multiple bacterial species including *Escherichia coli*, *Pseudomonas aeruginosa*, *Staphylococcus aureus*, *Salmonella enterica* (Enteritidis serovar) etc. These CQDs were also effective against a corneal disease bacterial keratitis induced by *S. aureus* in the rabbit model system [22]. Carbon dots synthesized from Aloe vera extract exhibited metal ion sensing as well as photosensitive bactericidal activity against *S. aureus* and *E. coli* [69]. CQDs with antiviral properties has also been designed which possess the capacity to enter the host cells and inhibit viral replication or act as carriers of antiviral agents. Curcumin based CQDs exhibited antiviral activity against different enteric coronaviruses [47,70].

Age-related macular degeneration, diabetic retinopathy and bacterial keratitis are among the major causes of ocular diseases leading to loss of vision, and different treatment approaches are associated with a major limitation of drug delivery to ocular posterior segment [71]. Kumar *et al.* thoroughly reviewed the application of CQDs in ocular imaging and eye disease treatments and suggested that biocompatible and eco-friendly nanomaterials derived from synthetic or natural polymers could be helpful to solve the drug delivery as well as safety concerns [73]. Various reports on gene therapy for retinal dystrophy, anti-angiogenic properties of CQDs, CQD based eye drop formulation and many more prove them as potential therapeutic molecules for ocular disease treatment [71-73].

Neurodegenerative diseases (NDs) like Alzheimer's, Parkinson's, Amyloid sclerosis, Huntington's disease and other disorders of central nervous system pose a substantial and continuously increasing burden on healthcare worldwide [74]. NDs are characterized by misfolded proteins or prion like proteins which include amyloid beta, α -synuclein, tau, mutant huntingtin protein etc. Guerrero *et al.* synthesized the sodium citrate derived CQDs and showed the inhibition of amyloidogenic fibril formation as well as disaggregation of mature fibrils into their monomers using a model amyloidogenic protein named as hen egg white lysozyme [75]. The studied CQDs exhibited low cytotoxicity in *in vitro* studies using SH-SY5Y cell line. CQDs prepared by Koppel *et al.* mitigated the lipopolysaccharide induced amyloid- β and human islet amyloid polypeptide plaque formation in zebra fish [76]. These reports suggest CQDs as potential prophylactic and therapeutic candidates for neurodegenerative diseases. However, majority of drugs developed for treatment of brain disorders face the major issue of crossing blood brain barrier. To enable the drug delivery or diagnostic probes to be delivered at specific sites, the CQDs take the advantage of their small size, and CQDs of size smaller than human capillaries can cross the blood brain barrier. Wang *et al.* developed nitrogen doped nanodots of carbon for fluorescence imaging which entered in glioma cells in *in vitro* as well as showed good fluorescence imaging of glioma in *in vivo* conditions [77].

In addition to cancer cell imaging or tracking, some CQDs with therapeutic potential against cancer have also been reported which has been discussed more in detail under theranostics section [78].

3.5 CQDs and Gene therapy

Gene therapy, being a rapidly flourishing technique has emerged as a great therapeutic approach for treatment of incurable diseases. This approach attempts to treat the ailment or strengthen body's resistance to disease by introduction of a new gene or replacement of a faulty gene. This broad treatment modality may be used to treat various recessively inherited genetic disorders like cystic fibrosis, sickle cell anaemia, muscular dystrophy and haemophilia as well as diseases associated with acquired genetic changes such as viral infections, cancers etc [79]. Effectiveness of the

approach depends on delivery of gene of interest to the nuclei of specific/ unhealthy cells with the help of vectors. Synthetic vectors offer a safer option as a vector as compared to viral based vectors being utilized for gene delivery, but synthetic vectors come with the limitation of low transfection efficiency in *in vivo* systems. CQDs synthesis with properties of low toxicity, lack of blinking, chemical stability and biocompatibility has been attempted for gene delivery, e.g. hyaluronic acid-based carbon dots developed by surface passivation with polyethylenimine exhibited the targeted cell imaging ability and showed the potential for effective transfection by releasing the DNA cargo into cytoplasm [80]. Cao *et al.* demonstrated the use of CQDs for delivery of pSOX9 plasmid in mouse embryonic fibroblasts. These CQDs with fluorescence property enabled intracellular tracking of nanoparticles and also induced chondrogenic differentiation in studied fibroblasts [81]. In another previous report, polyethylenimine based CQDs showed good biocompatibility and ability to act as labelling agent for gene delivery [82,83].

3.6 CQDs and Theranostics

In addition to above discussed applications, CQDs are being targeted in the field of theranostics which offers several benefits for both disease diagnosis and treatment. Theranostics are suggested to play an important role in personalized medicine, which is focussed on optimizing the effective treatment followed by minimal post-diagnosis delay [84,85]. The term theranostic has evolved to the term theragnostic as it better represents the combination of disease characterization (diagnosis) and treatment strategies, whereas theranostic is considered to provide more focus on disease characterization [86].

There are various studies demonstrating the application of CQDs in cancer theranostics such as ‘Large amino acid mimicking CQDs’ (LAAM-CQDs) for multiple *in vitro* and *in vivo* cancers, ‘Nitric oxide-releasing CQDs’ (NO-CQDs) for lung and colon cancers, and biocompatible ‘trichome tryptophan sorbitol CQDs’ (TC-WS-CQDs) for hepatocellular carcinoma [87-89]. Li and group targeted the amino acid transporters, specifically LAT-1 (large neutral amino acid transporter-1) for taking leverage in tumor theranostics and synthesized LAAM-CQDs. There are four LATs (LAT-1,2,3 and 4) out of which LAT-1 is known to be specifically upregulated in the tumor cells. Loading of CQDs (targeting LAT-1) with chemotherapeutic drugs increase the accumulation of drugs in targeted tumor cells, resulting in the increased treatment efficacy. The designed LAAM-CQDs were shown to have a high degree of tumor specificity and interaction with multiple tumors including brain tumors. A large cell panel including cancerous cell lines (lung, kidney, colon, cervical, ovary etc.), cancer stem cell cultures derived from patients, and non-cancerous cells were examined for LAAM-CQDs interaction, which suggested the potential of these CQDs to penetrate cancer cells irrespective of their origin. However, these CQDs showed limited penetration in non-cancer cells. *In vivo* brain tumors in U87MG glioma-bearing mice were also examined at different intervals in this study upon intravenous injections of LAAM TC-CQDs and by using NIR fluorescence imaging [90]. It was observed that, when the fluorescence signals were mostly detected in the brain, 8–12 hours after injection when the accumulation of LAAM TC-CQDs in the brain was at peak [87].

NO-CQDs were prepared by hydrodynamic method of β -cyclodextrin modification with functional groups and further incubation in alkaline environment with NO gas which resulted in particles with a range (0.2–1.1 $\mu\text{mol}/\text{mg}$) of different adjustable NO payloads and different surface functionalization (primary amine, hydroxyl). These CQDs were tested against Pa14c, SW480 and A549 cell lines which are used to mimic pancreatic, kidney and lung cancers, respectively and exhibited significant growth inhibition. The anticancer property of NO-CQDs was dependent upon the surface functionalization group and the payload capacity with maximum activity shown by modified primary amine functionalization with payload of $\sim 1.11 \mu\text{mol}/\text{mg}$ [88].

Further, TC-WS-CQDs were also synthesized upon hydrothermal break down of tryptophan and sorbitol in an environmentally safe manner. TC-WS-CQDs had a better targeting capacity into hepatocellular carcinoma cells than normal hepatocytes, which could enable early and effective tumor cell monitoring via fluorescence imaging. Tumor imaging and inhibition property TC-WS-CQDs were checked on Huh7 cell line as well as in a BALB/nu mice with induced hepatocellular carcinoma (HCC) and was found that *in vitro* and *in vivo* HCC prevention were improved simultaneously by these green fluorescence-emitting TC-WS-CQDs without the need for medication delivery as these nanoparticles produce large amounts of free radicals in targeted tumor cells. Large amounts of free radicals induce autophagy via activation of p53-AMPK pathway rendering the anticancer potential to these CQDs [89].

Enzyme based CQDs with nanozyme synthesized from coffee exhibited the glutathione peroxidase like activities and promoted the apoptosis of cancer cells. These coffee derived CQDs also reduced the size of tumor in mice bearing HepG2 induced tumor by recruiting the immune cells thus activating the anti-tumor immune system [78]. In another study CQDs synthesized from ginger selectively suppressed the growth of hepatocellular carcinoma cells (HepG2) by activating the cancer cell apoptosis while exhibiting low cytotoxicity to breast cancer, lung cancer and ovarian cancer cells [43]. CQDs based photodynamic therapy against cancers is also reported as potential tool for treating tumors and non-invasive lesions with less side effects. Magnetofluorescent Fe_3O_4 CQDs developed by Zhang *et al.* (named as SWCNTs-PEG- Fe_3O_4 @CQDs) exhibited the multiple roles of photodynamic, photo dermal and chemotherapy [46].

CQDs have also been reported to have application in mitochondria based theranostics, which could have utility in cancer as well other diseases. These CQDs has various benefits including high specificity, easy surface functionalization, great photostability, cost effective and simple synthesis, excellent photostability, applicability for long term imaging and negligible cytotoxicity over the commercially available mitochondrial tracking molecules. A study by Hua *et al.* reported the synthesis of fluorescence CQDs which target mitochondria via endocytosis mediated via caveolae and temperature dependent transport rather than being captured by lysosomes or endosomes in the cell [90]. Additionally, CQDs have application in infectious disease theranotics. N-doped CQDs from single step production showed antibacterial action against MRSA and *Staphylococcus*, even breaking down their cell walls; however, these CQDs were ineffective against *E. Coli*. Their mode of action shows that *Staphylococcus* bacteria bind to positively charged N-doped CQDs at particular places and interact with negatively charged bacteria. When applied to MRSA-caused wound infections, these N-doped CQDs showed outcomes comparable to vancomycin [91].

So, CQDs hold a great potential in theranostics and their integration in clinical theranostic could advance the personalized medicine to great extent including cancer, mitochondrial and infectious disease [92,93,94]. Ongoing research on nanotheranostics aims to develop CQDs with high functionality, less toxicity, high specificity and effective clinical translation.

4. Sustainable development and CQDs

The goal of sustainable development is to fulfill the requirements of current generations without compromising the capacity to fulfill the requirements of future generations. Embracing and following sustainable practices protect and preserves the planet's vitality also safeguarding human health and ensuring a harmonious coexistence for current and future generations [95]. Understanding the intersection of sustainability and health is crucial for developing comprehensive solutions that protect both ecosystems and human societies from the multiple effects of climate change, urbanization, and unrestrained consumerism.

Infectious and non-infectious diseases contribute significantly to the disease burden worldwide impacting economy, social life, environment and health security. Due to increased disease burden there is a continuous rise in global healthcare costs as well less loss of productivity. On the social front, in addition to mortality diseases also result in imbalanced economic status of an individual, impacting mental health due to suffering and social discrimination as well as disrupted necessary education. Further, the disease burden deprives individuals from necessary healthcare due to overwhelmed health facility upon emergence of diseases. Environment and other sustainable practices also suffer due to disease burden as it could lead to resource and efforts reallocation from planned strategies towards urgent healthcare needs. Thus, the impaired health and disease burden serve as one of the major roadblocks of sustainability for any nation or worldwide. To address this healthcare challenge, advancements in disease diagnosis and treatment strategies are required to achieve the early and correct diagnosis and thus reducing the suffering period by early treatment. Nanomaterial based strategies have gained much attention of the researchers to develop different entities with applications in the field of biomedical sciences. CQDs has various applications such as utility in effective drug delivery, gene delivery, imaging, biosensing and as well as serve as therapeutic molecules for cancer and other diseases which helps in achievement of sustainable development goal 3 (SDG3). Additionally, these materials also contribute to targets of other SDGs such as to achieve environment remediation (applications in water and air purification), energy conservation and storage, environmental sensing, waste disposal and management etc. which are not discussed in the current article.

5 CQDs and associated challenges

Although CQDs opened a promising window of applications in the biomedical field and are superior to some other types of quantum dots, however, they are still associated with challenges being faced by quantum dot technology [96,97]. These challenges are associated with synthesis, fabrication, size, specificity, toxicity, quantum yield, and reproducibility which need to be addressed to ensure their sustainable use in biomedicine. Synthesis and fabrication of the CQDs is challenging to ensure consistent size, shape, functionalization, and particles without any surface defect, which are further critical for the reproducibility of the promised results. Surface functionalization and different fabrication practices also impact the quantum yield (fluorescence emission efficacy) and toxicity index. CQDs can convert. More research is required to explore different fabrication techniques to increase the quantum yield of CQDs by rendering them low or no toxicity. Further, CQDs have shown great potential in biosensing, but with change in size impacts the specificity and sensitivity of sensors significantly, which could be addressed by developing the strategies to deliver CQDs with uniform properties. Additionally, the field of CQDs as biotags for testing allergies, antibiotic sensitivity, etc. is also less explored.

6 Conclusion

Carbon quantum dots (CQDs) have garnered significant attention in biomedicine due to their biocompatible and eco-friendly design.

Potential applications of CQDs in biomedicine include:

- Bioimaging
- Biosensing
- Drug delivery
- Disease treatment
- Gene delivery
- Theranostics

CQDs can also be utilized in the detection of food toxins and the formulation of pharmaceutical drugs, further contributing to biosensing and disease treatment. These applications of CQDs have the potential to significantly contribute to the achievement of sustainable development goals. CQDs offer a promising avenue to shape a healthier and more environmentally friendly future for both humanity and the planet. The exploration of CQDs in these various applications has the potential to lead to groundbreaking advancements that transcend disciplinary boundaries.

These advancements are essential for the well-being of present and future generations. Despite the potential, there are research gaps such as optimization of specific surface functionalization, limited clinical translation, etc that need to be addressed to understand the full scope of CQD formulation and applications and optimize their performance in various biomedical and environmental contexts.

References

1. Chotchoungchatchai, Somtanuek, Aniqah Islam Marshall, Woranan Witthayapipopsakul, Warisa Panichkriangkrai, Walaiporn Patcharanarumol, and Viroj Tangcharoensathien. "Primary health care and sustainable development goals." *Bulletin of the World Health Organization* 98, no. 11 (2020): 792.
2. Scheirer, Mary Ann, and James W. Dearing. "An agenda for research on the sustainability of public health programs." *American journal of public health* 101, no. 11 (2011): 2059-2067.
3. Hovlid, Einar, Oddbjørn Bukve, Kjell Haug, Aslak Bjarne Aslaksen, and Christian von Plessen. "Sustainability of healthcare improvement: what can we learn from learning theory?." *BMC health services research* 12 (2012): 1-13.
4. McGrath, Jane. "ADHD and Covid-19: Current roadblocks and future opportunities." *Irish journal of psychological medicine* 37, no. 3 (2020): 204-211.
5. Sharma, Abhishek, Niketa Thakur, Abhishek Thakur, Ankit Chauhan, Harpreet Babrah, and Abhishek Thakur Sr. "The Challenge of Antimicrobial Resistance in the Indian Healthcare System." *Cureus* 15, no. 7 (2023).
6. Murphy, Finbarr, Martin Mullins, Karena Hester, Allen Gelwick, Janeck J. Scott-Fordsmand, and Trevor Maynard. "Insuring nanotech requires effective risk communication." *Nature Nanotechnology* 12, no. 8 (2017): 717-719.
7. Zaytseva, Olga, and Günter Neumann. "Carbon nanomaterials: production, impact on plant development, agricultural and environmental applications." *Chemical and Biological Technologies in Agriculture* 3, no. 1 (2016): 1-26.
8. Waris, Abdul, Asmat Ali, Atta Ullah Khan, Muhammad Asim, Doaa Zamel, Kinza Fatima, Abdur Raziq et al. "Applications of various types of nanomaterials for the treatment of neurological disorders." *Nanomaterials* 12, no. 13 (2022): 2140.
9. Barenholz, Yechezkel Chezy. "Doxil®—The first FDA-approved nano-drug: Lessons learned." *Journal of controlled release* 160, no. 2 (2012): 117-134.
10. Mazumdar, Rajkumari, and Debajit Thakur. "Therapeutic Applications of Nanotechnology in the Prevention of Infectious Diseases." In *Emerging Nanomaterials for Advanced Technologies*, pp. 323-343. Cham: Springer International Publishing, 2022.

11. Verma, Anurakshee, Rizwan Arif, and Sapana Jadoun. "Synthesis, characterization, and application of modified textile nanomaterials." *Frontiers of Textile materials: Polymers, nanomaterials, enzymes, and advanced modification techniques* (2020): 167-187.
12. Azam, Nayab, Murtaza Najabat Ali, and Tooba Javaid Khan. "Carbon quantum dots for biomedical applications: review and analysis." *Frontiers in Materials* 8 (2021): 700403.
13. Wang, Ying, Shao-Kai Sun, Yang Liu, and Zhanzhan Zhang. "Advanced hitchhiking nanomaterials for biomedical applications." *Theranostics* 13, no. 14 (2023): 4781.
14. Bozrova, S. V., M. A. Baryshnikova, Z. A. Sokolova, I. R. Nabiev, and A. V. Sukhanova. "In vitro cytotoxicity of CdSe/ZnS quantum dots and their interaction with biological systems." *KnE Energy* (2018): 58-63.
15. Molaei, Mohammad Jafar. "A review on nanostructured carbon quantum dots and their applications in biotechnology, sensors, and chemiluminescence." *Talanta* 196 (2019): 456-478.
16. Zhu, Shoujun, Junhu Zhang, Chunyan Qiao, Shijia Tang, Yunfeng Li, Wenjing Yuan, Bo Li et al. "Strongly green-photoluminescent graphene quantum dots for bioimaging applications." *Chemical communications* 47, no. 24 (2011): 6858-6860.
17. Peng, Juan, Wei Gao, Bipin Kumar Gupta, Zheng Liu, Rebeca Romero-Aburto, Liehui Ge, Li Song et al. "Graphene quantum dots derived from carbon fibers." *Nano letters* 12, no. 2 (2012): 844-849.
18. Fan, Zetan, Yunchao Li, Xiaohong Li, Louzhen Fan, Shixin Zhou, Decai Fang, and Shihe Yang. "Surrounding media sensitive photoluminescence of boron-doped graphene quantum dots for highly fluorescent dyed crystals, chemical sensing and bioimaging." *Carbon* 70 (2014): 149-156.
19. Song, Yang, Xu Yan, Zhaohui Li, Lingbo Qu, Chengzhou Zhu, Ranfeng Ye, Suiqiong Li, Dan Du, and Yuehe Lin. "Highly photoluminescent carbon dots derived from linseed and their applications in cellular imaging and sensing." *Journal of Materials Chemistry B* 6, no. 19 (2018): 3181-3187.
20. Yang, Sheng-Tao, Xin Wang, Haifang Wang, Fushen Lu, Pengju G. Luo, Li Cao, Mohammed J. Meziani et al. "Carbon dots as nontoxic and high-performance fluorescence imaging agents." *The Journal of Physical Chemistry C* 113, no. 42 (2009): 18110-18114.
21. Cao, Li, Xin Wang, Mohammed J. Meziani, Fushen Lu, Haifang Wang, Pengju G. Luo, Yi Lin et al. "Carbon dots for multiphoton bioimaging." *Journal of the American Chemical Society* 129, no. 37 (2007): 11318-11319.
22. Jiang, Kai, Shan Sun, Ling Zhang, Yue Lu, Aiguo Wu, Congzhong Cai, and Hengwei Lin. "Red, green, and blue luminescence by carbon dots: full-color emission tuning and multicolor cellular imaging." *Angewandte chemie* 127, no. 18 (2015): 5450-5453.
23. Shi, Lihong, Yanyan Li, Xiaofeng Li, Xiangping Wen, Guomei Zhang, Jun Yang, Chuan Dong, and Shaomin Shuang. "Facile and eco-friendly synthesis of green fluorescent carbon nanodots for applications in bioimaging, patterning and staining." *Nanoscale* 7, no. 16 (2015): 7394-7401.
24. Su, Wen, Hao Wu, Huimin Xu, Yang Zhang, Yunchao Li, Xiaohong Li, and Louzhen Fan. "Carbon dots: a booming material for biomedical applications." *Materials Chemistry Frontiers* 4, no. 3 (2020): 821-836.
25. Shang, Weihua, Xiaoyan Zhang, Mo Zhang, Zetan Fan, Ying Sun, Mei Han, and Louzhen Fan. "The uptake mechanism and biocompatibility of graphene quantum dots with human neural stem cells." *Nanoscale* 6, no. 11 (2014): 5799-5806.
26. Guo, Ruihua, Shixin Zhou, Yunchao Li, Xiaohong Li, Louzhen Fan, and Nicolas H. Voelcker. "Rhodamine-functionalized graphene quantum dots for detection of Fe³⁺ in cancer stem cells." *ACS applied materials & interfaces* 7, no. 43 (2015): 23958-23966.
27. Huang, Caoxing, Huiling Dong, Yan Su, Yan Wu, Robert Narron, and Qiang Yong. "Synthesis of carbon quantum dot nanoparticles derived from byproducts in bio-refinery process for cell imaging and in vivo bioimaging." *Nanomaterials* 9, no. 3 (2019): 387.

28. Yang, Sheng-Tao, Li Cao, Pengju G. Luo, Fushen Lu, Xin Wang, Haifang Wang, Mohammed J. Meziani, Yuanfang Liu, Gang Qi, and Ya-Ping Sun. "Carbon dots for optical imaging in vivo." *Journal of the American Chemical Society* 131, no. 32 (2009): 11308-11309.
29. Cao, Li, Sheng-Tao Yang, Xin Wang, Pengju G. Luo, Jia-Hui Liu, Sushant Sahu, Yamin Liu, and Ya-Ping Sun. "Competitive performance of carbon "quantum" dots in optical bioimaging." *Theranostics* 2, no. 3 (2012): 295.
30. Luo, Pengju G., Sushant Sahu, Sheng-Tao Yang, Sumit K. Sonkar, Jinping Wang, Haifang Wang, Gregory E. LeCroy, Li Cao, and Ya-Ping Sun. "Carbon "quantum" dots for optical bioimaging." *Journal of Materials Chemistry B* 1, no. 16 (2013): 2116-2127.
31. Li, Shuhua, Shixin Zhou, Yunchao Li, Xiaohong Li, Jia Zhu, Louzhen Fan, and Shihe Yang. "Exceptionally high payload of the IR780 iodide on folic acid-functionalized graphene quantum dots for targeted photothermal therapy." *ACS applied materials & interfaces* 9, no. 27 (2017): 22332-22341.
32. Zhu, Hua, Chuanke Zhao, Fei Liu, Lixin Wang, Junnan Feng, Chengchao Shou, and Zhi Yang. "125I-F56 Peptide as Radioanalysis Agent Targeting VEGFR1 in Mice Xenografted with Human Gastric Tumor." *ACS Medicinal Chemistry Letters* 8, no. 2 (2017): 266-269.
33. Liu, Fei, Teli Liu, Xiaoxia Xu, Xiaoyi Guo, Nan Li, Chiyi Xiong, Chun Li, Hua Zhu, and Zhi Yang. "Design, Synthesis, and Biological Evaluation of 68Ga-DOTA-PA1 for Lung Cancer: A Novel PET Tracer for Multiple Somatostatin Receptor Imaging." *Molecular Pharmaceutics* 15, no. 2 (2018): 619-628.
34. Ji, Chunyu, Yiqun Zhou, Roger M. Leblanc, and Zhili Peng. "Recent developments of carbon dots in biosensing: A review." *ACS sensors* 5, no. 9 (2020): 2724-2741.
35. Wu, Xiaoxue, Shan Sun, Yuhui Wang, Jiali Zhu, Kai Jiang, Yumin Leng, Qinghai Shu, and Hengwei Lin. "A fluorescent carbon-dots-based mitochondria-targetable nanoprobe for peroxynitrite sensing in living cells." *Biosensors and Bioelectronics* 90 (2017): 501-507.
36. Bhattacharya, Sagarika, Rhitajit Sarkar, Sukhendu Nandi, Angel Porgador, and Raz Jelinek. "Detection of reactive oxygen species by a carbon-dot-ascorbic acid hydrogel." *Analytical chemistry* 89, no. 1 (2017): 830-836.
37. Lu, Shuaimin, Guoliang Li, Zhengxian Lv, Nannan Qiu, Weiheng Kong, Peiwei Gong, Guang Chen et al. "Facile and ultrasensitive fluorescence sensor platform for tumor invasive biomarker β -glucuronidase detection and inhibitor evaluation with carbon quantum dots based on inner-filter effect." *Biosensors and Bioelectronics* 85 (2016): 358-362.
38. Yuan, Fanglong, Ling Ding, Yunchao Li, Xiaohong Li, Louzhen Fan, Shixin Zhou, Decai Fang, and Shihe Yang. "Multicolor fluorescent graphene quantum dots colorimetrically responsive to all-pH and a wide temperature range." *Nanoscale* 7, no. 27 (2015): 11727-11733.
39. Wang, Chuanxi, Kaili Jiang, Qian Wu, Jiapeng Wu, and Chi Zhang. "Green Synthesis of Red-Emitting Carbon Nanodots as a Novel "Turn-on" Nanothermometer in Living Cells." *Chemistry—A European Journal* 22, no. 41 (2016): 14475-14479.
40. Raveendran, Varsha, and Renuka Neeroli Kizhakayil. "Fluorescent carbon dots as biosensor, green reductant, and biomarker." *ACS omega* 6, no. 36 (2021): 23475-23484.
41. Kour, Ravinder, Sandeep Arya, Sheng-Joue Young, Vinay Gupta, Pankaj Bandhoria, and Ajit Khosla. "Recent advances in carbon nanomaterials as electrochemical biosensors." *Journal of The Electrochemical Society* 167, no. 3 (2020): 037555.
42. Hua, Xian-Wu, Yan-Wen Bao, Zhan Chen, and Fu-Gen Wu. "Carbon quantum dots with intrinsic mitochondrial targeting ability for mitochondria-based theranostics." *Nanoscale* 9, no. 30 (2017): 10948-10960.
43. Lee, Hyun Uk, So Young Park, Eun Sik Park, Byoungchul Son, Soon Chang Lee, Jae Won Lee, Young-Chul Lee et al. "Photoluminescent carbon nanotags from harmful cyanobacteria for drug delivery and imaging in cancer cells." *Scientific reports* 4, no. 1 (2014): 4665.
44. Molaei, Mohammad Jafar. "Carbon quantum dots and their biomedical and therapeutic applications: a review." *RSC advances* 9, no. 12 (2019): 6460-6481.

45. Khan, M. Shahnawaz, Sunil Pandey, Abou Talib, Mukesh Bhaiare, and Hui-Fen Wu. "Controlled delivery of dopamine hydrochloride using surface modified carbon dots for neuro diseases." *Biophysical Journal* 108, no. 2 (2015): 331a-332a.
46. Zhang, Ming, Ping Yuan, Ninglin Zhou, Yutian Su, Maoni Shao, and Cheng Chi. "pH-Sensitive N-doped carbon dots–heparin and doxorubicin drug delivery system: preparation and anticancer research." *RSC advances* 7, no. 15 (2017): 9347-9356.
47. Nair, Akhila, Jozef T. Haponiuk, Sabu Thomas, and Sreeraj Gopi. "Natural carbon-based quantum dots and their applications in drug delivery: A review." *Biomedicine & Pharmacotherapy* 132 (2020): 110834.
48. Praseetha, P. K., B. V. Vibala, K. Sreedevy, and S. Vijayakumar. "Aloe-vera conjugated natural Carbon Quantum dots as Bio-enhancers to accelerate the repair of chronic wounds." *Industrial Crops and Products* 174 (2021): 114152.
49. Hu, Chaoshuai, Yaming Zhu, and Xuefei Zhao. "On-off-on nanosensors of carbon quantum dots derived from coal tar pitch for the detection of Cu²⁺, Fe³⁺, and L-ascorbic acid." *Spectrochimica Acta Part A: Molecular and Biomolecular Spectroscopy* 250 (2021): 119325.
50. Wu, Lina, Yaoran Gao, Chengfei Zhao, Dandan Huang, Wenxin Chen, Xinhua Lin, Ailin Liu, and Liqing Lin. "Synthesis of curcumin-quaternized carbon quantum dots with enhanced broad-spectrum antibacterial activity for promoting infected wound healing." *Biomaterials Advances* 133 (2022): 112608.
51. Hou, Juan, Wei Wang, Tianyu Zhou, Bo Wang, Huiyu Li, and Lan Ding. "Synthesis and formation mechanistic investigation of nitrogen-doped carbon dots with high quantum yields and yellowish-green fluorescence." *Nanoscale* 8, no. 21 (2016): 11185-11193.
52. Liu, Yang, Yanan Liu, Mira Park, Soo-Jin Park, Yifan Zhang, Md Rashedunnabi Akanda, Byung-Yong Park, and Hak Yong Kim. "Green synthesis of fluorescent carbon dots from carrot juice for in vitro cellular imaging." *Carbon Letters (Carbon Lett.)* 21 (2017): 61-67.
53. Sahu, Swagatika, Birendra Behera, Tapas K. Maiti, and Sasmita Mohapatra. "Simple one-step synthesis of highly luminescent carbon dots from orange juice: application as excellent bio-imaging agents." *Chemical communications* 48, no. 70 (2012): 8835-8837.
54. Zhang, Jing-Hui, Aping Niu, Jing Li, Jian-Wei Fu, Qun Xu, and De-Sheng Pei. "In vivo characterization of hair and skin derived carbon quantum dots with high quantum yield as long-term bioprobes in zebrafish." *Scientific reports* 6, no. 1 (2016): 37860.
55. Gedda, Gangaraju, Sri Amrutha Sankaranarayanan, Chandra Lekha Putta, Krishna Kanthi Gudimella, Aravind Kumar Rengan, and Wubshet Mekonnen Girma. "Green synthesis of multi-functional carbon dots from medicinal plant leaves for antimicrobial, antioxidant, and bioimaging applications." *Scientific Reports* 13, no. 1 (2023): 6371.
56. Doshi, Krushangi, and Alka A. Mungray. "Bio-route synthesis of carbon quantum dots from tulsi leaves and its application as a draw solution in forward osmosis." *Journal of Environmental Chemical Engineering* 8, no. 5 (2020): 104174.
57. Cui, Lin, Xin Ren, Mengtao Sun, Haiyan Liu, and Lixin Xia. "Carbon dots: Synthesis, properties and applications." *Nanomaterials* 11, no. 12 (2021): 3419.
58. Kang, Chao, Ying Huang, Hui Yang, Xiu Fang Yan, and Zeng Ping Chen. "A review of carbon dots produced from biomass wastes." *Nanomaterials* 10, no. 11 (2020): 2316.
59. Fahmi, Mochamad Zakki, Abdul Haris, Ahmadi Jaya Permana, Denika Liyan Nor Wibowo, Bambang Purwanto, Yatim Lailun Nikmah, and Adi Idris. "Bamboo leaf-based carbon dots for efficient tumor imaging and therapy." *RSC advances* 8, no. 67 (2018): 38376-38383.
60. Chunduri, L. A., Aditya Kurdekar, Sandeep Patnaik, B. Vishnu Dev, Tanu Mimani Rattan, and Venkataramaniah Kamiseti. "Carbon quantum dots from coconut husk: evaluation for antioxidant and cytotoxic activity." *Materials Focus* 5, no. 1 (2016): 55-61.

61. Mubarik, Shamroza, Nawal Qureshi, Zainab Sattar, Aqeela Shaheen, Ambreen Kalsoom, Marryam Imran, and Farzana Hanif. "Synthetic approach to rice waste-derived carbon-based nanomaterials and their applications." *Nanomanufacturing* 1, no. 3 (2021): 109-159.
62. Chu, Ling, Yu Zhang, Leli He, Qingwu Shen, Mingqian Tan, and Yanyang Wu. "Carbon Quantum Dots from Roasted Coffee Beans: Their Degree and Mechanism of Cytotoxicity and Their Rapid Removal Using a Pulsed Electric Field." *Foods* 12, no. 12 (2023): 2353.
63. Elango, Duraisamy, Jeyakumar Saranya Packialakshmi, Velu Manikandan, and Palaniyappan Jayanthi. "Sustainable synthesis of carbon quantum dots from shrimp shell and its emerging applications." *Materials Letters* 312 (2022): 131667.
64. Mehta, Vaibhavkumar N., Shiva Shankaran Chettiar, Jigna R. Bhamore, Suresh Kumar Kailasa, and Ramesh M. Patel. "Green synthetic approach for synthesis of fluorescent carbon dots for lisinopril drug delivery system and their confirmations in the cells." *Journal of fluorescence* 27 (2017): 111-124.
65. Bu, Lingli, Tao Luo, Huanjun Peng, Ling Li, Dengying Long, Jingdong Peng, and Jing Huang. "One-step synthesis of N-doped carbon dots, and their applications in curcumin sensing, fluorescent inks, and super-resolution nanoscopy." *Microchimica Acta* 186 (2019): 1-12.
66. Ensafi, Ali A., S. Hghighat Sefat, N. Kazemifard, B. Rezaei, and F. Moradi. "A novel one-step and green synthesis of highly fluorescent carbon dots from saffron for cell imaging and sensing of prilocaine." *Sensors and Actuators B: Chemical* 253 (2017): 451-460.
67. Shao, Yingying, Caoyuan Zhu, Zhifei Fu, Kui Lin, Yidan Wang, Yanxu Chang, Lifeng Han, Haiyang Yu, and Fei Tian. "Green synthesis of multifunctional fluorescent carbon dots from mulberry leaves (*Morus alba* L.) residues for simultaneous intracellular imaging and drug delivery." *Journal of Nanoparticle Research* 22 (2020): 1-11.
68. Nie, Xiaolin, Chenyu Jiang, Shuanglin Wu, Wangbingfei Chen, Pengfei Lv, Qingqing Wang, Jingyan Liu et al. "Carbon quantum dots: A bright future as photosensitizers for in vitro antibacterial photodynamic inactivation." *Journal of Photochemistry and Photobiology B: Biology* 206 (2020): 111864.
69. Devi, Pooja, Anupma Thakur, Sanjeev K. Bhardwaj, Shefali Saini, Prachi Rajput, and Praveen Kumar. "Metal ion sensing and light activated antimicrobial activity of aloe-vera derived carbon dots." *Journal of Materials Science: Materials in Electronics* 29, no. 20 (2018): 17254-17261.
70. Ting, Du, Nan Dong, Liurong Fang, Jian Lu, Jing Bi, Shaobo Xiao, and Heyou Han. "Multisite inhibitors for enteric coronavirus: antiviral cationic carbon dots based on curcumin." *ACS Applied Nano Materials* 1, no. 10 (2018): 5451-5459.
71. Kumar, Vijay Bhooshan, Ifat Sher, Sigal Rencus-Lazar, Ygal Rotenstreich, and Ehud Gazit. "Functional carbon quantum dots for ocular imaging and therapeutic applications." *Small* 19, no. 7 (2023): 2205754.
72. Shereema, R. M., T. V. Sruthi, VB Sameer Kumar, T. P. Rao, and S. Sharath Shankar. "Angiogenic profiling of synthesized carbon quantum dots." *Biochemistry* 54, no. 41 (2015): 6352-6356.
73. Biswal, Manas R., and Sofia Bhatia. "Carbon dot nanoparticles: exploring the potential use for gene delivery in ophthalmic diseases." *Nanomaterials* 11, no. 4 (2021): 935.
74. Sharma, Anuradha, Payal Bajaj, Anmol Bhandari, and Gurcharan Kaur. "From ayurvedic folk medicine to preclinical neurotherapeutic role of a miraculous herb, *Tinospora cordifolia*." *Neurochemistry International* 141 (2020): 104891.
75. Guerrero, Erick Damian, Angela Marlene Lopez-Velazquez, Jyoti Ahlawat, and Mahesh Narayan. "Carbon quantum dots for treatment of amyloid disorders." *ACS applied nano materials* 4, no. 3 (2021): 2423-2433.
76. Koppel, Kairi, Huayuan Tang, Ibrahim Javed, Mehrdad Parsa, Monika Mortimer, Thomas P. Davis, Sijie Lin, Alan L. Chaffee, Feng Ding, and Pu Chun Ke. "Elevated amyloidoses of human IAPP and amyloid beta by lipopolysaccharide and their mitigation by carbon quantum dots." *Nanoscale* 12, no. 23 (2020): 12317-12328.

77. Wang, Yi, Ying Meng, Shanshan Wang, Chengyi Li, Wei Shi, Jian Chen, Jianxin Wang, and Rongqin Huang. "Direct Solvent-Derived Polymer-Coated Nitrogen-Doped Carbon Nanodots with High Water Solubility for Targeted Fluorescence Imaging of Glioma." *Small* 11, no. 29 (2015): 3575-3581.
78. Yao, Lu, Mei-Mei Zhao, Qian-Wei Luo, Yi-Chi Zhang, Ting-Ting Liu, Zhuo Yang, Min Liao, Pengfei Tu, and Ke-Wu Zeng. "Carbon quantum dots-based nanozyme from coffee induces cancer cell ferroptosis to activate antitumor immunity." *ACS nano* 16, no. 6 (2022): 9228-9239.
79. Zhang, Ming, Wentao Wang, Yingjun Cui, Xiaohong Chu, Baohong Sun, Ninglin Zhou, and Jian Shen. "Magnetofluorescent Fe₃O₄/carbon quantum dots coated single-walled carbon nanotubes as dual-modal targeted imaging and chemo/photodynamic/photothermal triple-modal therapeutic agents." *Chemical Engineering Journal* 338 (2018): 526-538.
80. Gonçalves, Giulliana Augusta Rangel, and Raquel de Melo Alves Paiva. "Gene therapy: advances, challenges and perspectives." *Einstein (Sao Paulo)* 15 (2017): 369-375.
81. Wang, Hai-Jiao, Ji Zhang, Yan-Hong Liu, Tian-Ying Luo, Xi He, and Xiao-Qi Yu. "Hyaluronic acid-based carbon dots for efficient gene delivery and cell imaging." *RSC advances* 7, no. 25 (2017): 15613-15624.
82. Cao, Xia, Jianping Wang, Wenwen Deng, Jingjing Chen, Yan Wang, Jie Zhou, Pan Du et al. "Photoluminescent cationic carbon dots as efficient non-viral delivery of plasmid SOX9 and chondrogenesis of fibroblasts." *Scientific reports* 8, no. 1 (2018): 7057.
83. Hu, Liming, Yun Sun, Shengliang Li, Xiaoli Wang, Kelei Hu, Lirong Wang, Xing-jie Liang, and Yan Wu. "Multifunctional carbon dots with high quantum yield for imaging and gene delivery." *Carbon* 67 (2014): 508-513.
84. Li, Xingshu, Jihoon Kim, Juyoung Yoon, and Xiaoyuan Chen. "Cancer-associated, stimuli-driven, turn on theranostics for multimodality imaging and therapy." *Advanced Materials* 29, no. 23 (2017): 1606857.
85. Kalash, Rajendrakumar Santhosh, Vinoth Kumar Lakshmanan, Chong-Su Cho, and In-Kyu Park. "Theranostics." In *Biomaterials Nanoarchitectonics*, William Andrew Publishing, (2016): 197-215.
86. Frangos, Savvas, and John R. Buscombe. "Why should we be concerned about a "g"?" *European Journal of Nuclear Medicine and Molecular Imaging* 46, no. 2 (2019): 519-519.
87. Li, Shuhua, Wen Su, Hao Wu, Ting Yuan, Chang Yuan, Jun Liu, Gang Deng et al. "Targeted tumour theranostics in mice via carbon quantum dots structurally mimicking large amino acids." *Nature biomedical engineering* 4, no. 7 (2020): 704-716.
88. Wang, Yang, Jun Chen, Jiekang Tian, Guanchen Wang, Weikang Luo, Zebing Huang, Yan Huang, Ning Li, Mingming Guo, and Xuegong Fan. "Tryptophan-sorbitol based carbon quantum dots for theranostics against hepatocellular carcinoma." *Journal of nanobiotechnology* 20, no. 1 (2022): 78.
89. Jin, Haibao, Evan S. Feura, and Mark H. Schoenfisch. "Theranostic activity of nitric oxide-releasing carbon quantum dots." *Bioconjugate Chemistry* 32, no. 2 (2021): 367-375.
90. Hua, Xian-Wu, Yan-Wen Bao, Zhan Chen, and Fu-Gen Wu. "Carbon quantum dots with intrinsic mitochondrial targeting ability for mitochondria-based theranostics." *Nanoscale* 9, no. 30 (2017): 10948-10960.
91. Zhao, Chengfei, Lina Wu, Xuewen Wang, Shaohuang Weng, Zhipeng Ruan, Qicai Liu, Liqing Lin, and Xinhua Lin. "Quaternary ammonium carbon quantum dots as an antimicrobial agent against gram-positive bacteria for the treatment of MRSA-infected pneumonia in mice." *Carbon* 163 (2020): 70-84.
92. Abioye, Kunmi Joshua, Noorfidza Yub Harun, Suriati Sufian, Mohammad Yusuf, Muhammad Irfan Khan, Ahmad Hussaini Jagaba, Surajudeen Sikiru et al. "Kinetics and thermodynamic analysis of palm oil decanter cake and alum sludge combustion for bioenergy production." *Sustainable Chemistry and Pharmacy* 36 (2023): 101306.
93. Falsafi, Seid Reza, Fuat Topuz, Dagmara Bajer, Zahra Mohebi, Maryam Shafieiuon, Hajar Heydari, Shruti Rawal et al. "Metal nanoparticles and carbohydrate polymers team up to improve biomedical outcomes." *Biomedicine & Pharmacotherapy* 168 (2023): 115695.

94. Chen, Xiangyu, Shifa Wang, Yujia Jin, Maoyuan Li, Huajing Gao, Hua Yang, Leiming Fang et al. "CQDs drives CeO₂/PbFe₁₂O₁₉ photocatalysts for oxytetracycline hydrochloride removal by photoinduction and magnetic recovery." *Materials Science in Semiconductor Processing* 169 (2024): 107881.
95. Ruggerio, Carlos Alberto. "Sustainability and sustainable development: A review of principles and definitions." *Science of the Total Environment* 786 (2021): 147481.
96. Chandekar, Kamlesh V., S. P. Yadav, Shamal Chinke, and Mohd Shkir. "Impact of Co-doped NiFe₂O₄ (Co_xNi_{1-x}Fe₂O₄) nanostructures prepared by co-precipitation route on the structural, morphological, surface, and magnetic properties." *Journal of Alloys and Compounds* 966 (2023): 171556.
97. Shahcheraghi, Seyed H., Jamshid Ayatollahi, Marzieh Lotfi, Alaa AA Aljabali, Mazhar S. Al-Zoubi, Pritam K. Panda, Vijay Mishra et al. "Gene therapy for neuropsychiatric disorders: Potential targets and tools." *CNS & Neurological Disorders-Drug Targets (Formerly Current Drug Targets-CNS & Neurological Disorders)* 22, no. 1 (2023): 51-65.